

Multitemp PF CP 201

Multitemp PF CP 201 is a phenolic paper.

IEC 60893: PF CP 201
 DIN 7735: Hp 2061
 Nema LI 1: XXP

Properties	Units	
Flexural strength	MPa	150
Impact strength	kJ/m ²	20
Notched impact strength	kJ/m ²	15
Tensile strength	MPa	120
Compressive strength	MPa	150
Interlaminar strength	N	2000
Modulus of Elasticity	MPa	7000
Resistance between plugs	-	-
High voltage strength	KV	15/15
Dissipation factor	-	-
Dielectrical constant	-	5
Tracking resistance	-	100
Electrical corrosion	-	-
Limit temperature	°C	120
Thermal conductivity	W/m K	0,2
Thermal expansion factor	10 ⁻⁶ /°C	20-40
Thermal Class	-	E
Glow Resistance	-	2b
Density	g/cm ³	1,3-1,4
Water absorption	mg	660
Flame Resistance	-	-

Colour	-	Dark Brown
--------	---	------------

Availability:

Sheet: Size: 1220 x 2440 mm
 Thickness: 0,5 - 180 mm